

## REPORT DOCUMENTATION PAGE

0337

DURCS  
of this  
Person

Public reporting burden for this collection of information is estimated to average 1 hour per response, including gathering and maintaining the data needed, and completing and reviewing the collection of information. Send comments regarding this burden estimate or any other aspect of this collection of information, including suggestions for reducing this burden, to Washington Headquarters Service, Paperwork Reduction Project (0704-0188), Davis Highway, Suite 1204, Arlington, VA 22202-4302, and to the Office of Management and Budget, Paperwork Reduction Project (0704-0188), Washington, DC 20503.

1. AGENCY USE ONLY (Leave blank)	2. REPORT DATE	3. REPORT TYPE AND DATES COVERED Final 30 Jun 94 to 29 Jun 97	
4. TITLE AND SUBTITLE (AASERT 94-158) Vortex Dynamics in lightly-Doped Films of High Temperature Superconductors		5. FUNDING NUMBERS  61103D 3484/TS	
6. AUTHOR(S)  Professor Lemberger		8. PERFORMING ORGANIZATION REPORT NUMBER	
7. PERFORMING ORGANIZATION NAME(S) AND ADDRESS(ES) Ohio State University Research Foundation 1960 Kenny Road columbus OH 43210-1063		10. SPONSORING/MONITORING AGENCY REPORT NUMBER  F49620-94-1-0274	
9. SPONSORING/MONITORING AGENCY NAME(S) AND ADDRESS(ES)  AFOSR/NE 110 Duncan Ave RMB115 Bolling AFB DC 20332-8050		11. SUPPLEMENTARY NOTES	
12a. DISTRIBUTION/AVAILABILITY STATEMENT  APPROVAL FOR PUBLIC RELEASE: DISTRIBUTION UNLIMITED		12b. DISTRIBUTION CODE	
13. ABSTRACT (Maximum 200 words)			

19980511 066

Evidence is presented supporting the view that the inductance of vortices in films is due to columnar defects. The temperature dependence of the pinning strength is dominated by thermal supercurrent, or "phase", fluctuations rather than by the mean-field temperature dependence of basic superconducting quantities like the Helmholtz free energy and the magnetic penetration depth.

14. SUBJECT TERMS			15. NUMBER OF PAGES
			16. PRICE CODE
17. SECURITY CLASSIFICATION OF REPORT UNCLASSIFIED	18. SECURITY CLASSIFICATION OF THIS PAGE UNCLASSIFIED	19. SECURITY CLASSIFICATION OF ABSTRACT UNCLASSIFIED	20. LIMITATION OF ABSTRACT UL

1



FAX NUMBER 202.404.7951

$P_{KA}$

Sheets to follow 3

RE: - 94-1-0274  
Final Report.

**e-mail: [rundle.1@osu.edu](mailto:rundle.1@osu.edu)**

Final Technical Report for ASSERT grant F49620-94-1-0274, 6/30/94 - 6/29/97.

Due: 9/1/97.

Thomas R. Lemberger, P.I.

Page 1, Section 13, *Abstract*:

This is the final technical report for ASSERT grant F49620-94-1 0274, T.R. Lemberger, Principal Investigator.

We have taken a great deal of data and now understand that the inductance of vortices in films is due to columnar defects, and that the temperature dependence of the pinning strength is dominated by thermal supercurrent, or "phase", fluctuations rather than by the mean-field temperature dependence of basic superconducting quantities like the Helmholtz free energy and the magnetic penetration depth. We have the most data on pure YBCO films and are extending our measurements to oxygen-depleted and chemically doped YBCO films as well as to other materials. In this way we will determine how to improve the vortex pinning properties of YBCO films *via* chemical substitutions.

Main body of report, per AFOSR amendment No. 2 dated 03/27/89.

**a) Objectives.**

Our primary objective is to understand the dynamics of superconducting vortices created in films of the high-temperature superconductor,  $\text{YBa}_2\text{Cu}_3\text{O}_{7-x}$ , by application of a magnetic field perpendicular to the film. Of particular interest is the range of fields and temperatures away from the vortex-glass melting transition. Subsidiary objectives included development of a novel apparatus and the associated numerical inversion routines to obtain the relevant vortex parameters of pinning strength and viscosity from measurement of the mutual inductance of coils on opposite sides of the film. The technique permits precise and accurate measurements on films that are unpatterned, and it avoids edge effects.

The technical goal of this project is to determine how to tailor the properties of films of  $\text{YBa}_2\text{Cu}_3\text{O}_{7-x}$  to minimize electrical dissipation when such films are operated at high currents in sizable ambient magnetic fields. At present, it is known that YBCO films can be tremendously effective in pinning superconducting vortices, but it is not known what particular feature of the film provides the pinning or whether this mechanism can be enhanced via chemical doping. We intend to find out.

**b) Status of research effort.**

The experiment is fully operational. We are taking and analyzing data as fast as we can. Our results are providing a much fuller picture of the evolution of vortex pinning with field and temperature than has been produced previously. We have discovered that thermal phase

SEN1 BY BUCKETE RESEARCH 11-21-97 2-401M 030N 014 2024010 202 404 1001M 07 7

(supercurrent) fluctuations dominate the dependence of pinning strength on temperature not only in the critical regime near the vortex glass melting transition, but also at the lowest temperatures we have studied, namely, 4K. This is the primary effort of graduate student, Aaron Pesetski. Assistance on film fabrication is provided by another graduate student, Brent Boyce, and undergraduate student James Baumgardner. Due to the unanticipated departure of the original student on the project, the flow of papers is just beginning.

**c) Publications.**

*"Inductive response of vortices in  $Y_1Ba_2Cu_3O_7$  and  $Sr_1B_2C_2O$  films,"* Anne E. Cunningham, Master's Thesis, Ohio State University, August, 1995.

*"Vortex pinning in the frozen vortex lattice in  $YBa_2Cu_3O_{7-\delta}$  films,"* D.G. Xenikos, A.E. Cunningham, T.R. Lemberger, L. Hou, and M.W. McElfresh, Phys. Rev. B 53, 9453 (1996).

*"Numerical modeling and experimental considerations for a two-coil apparatus to find the complex conductivity of finite radius thin films,"* Stefan J. Turneaure, Aaron Pesetski, and T.R. Lemberger, currently in final draft form, to be submitted to J. Appl. Phys.

*"Influence of thermal phase fluctuations on the T dependence of the vortex pinning strength in YBCO films,"* Aaron Pesetski, Kathleen M. Paget, Brent R. Boyce, and T.R. Lemberger, in preparation. To be submitted to Phys. Rev. B.

**d) Personnel.**

Thomas R. Lemberger, Prof. of Physics, Principal Investigator.

Anne E. Cunningham, Graduate Research Associate, Physics Ph.D. program.

Aaron A. Pesetski, Graduate Research Associate, Physics Ph.D. program.

Brent R. Boyce, Graduate Research Associate, Physics Ph.D. program.

James E. Baumgardner II, Undergraduate, Honors Program.

**e) Interactions.**

**Presentations:**

"Effects of dopants on electrodynamics in oxide superconductors," a seminar given at Wayne State University, April, 1995; Univ. of Cincinnati, May, 1995.

APenetration depth studies on pure and doped superconducting YBCO,@ a seminar given at Ohio State Univ., Oct., 1996; U. Toledo, Nov. 1996; Notre Dame Univ., Nov. 1996.

*"Penetration depth studies in pure and doped  $\text{YBa}_2\text{Cu}_3\text{O}_{7-x}$  films," SPIE conference, "Oxide Superconductor Physics and Nanoengineering II," San Jose, CA, January, 1996.*

*"Evidence for thermal phase fluctuations in the magnetic penetration depth of YBCO at low temperatures," March Meeting of the APS, Kansas City, MO, 1997.*

*"Dopants (not impurities) in superconductors," given at the symposium in honor of the retirement of Donald M. Ginsberg, Univ. of Illinois-Urbana, April, 1997.*

**Consultative functions:**

Sample and measurement exchange with Drs. Timothy Peterson and Rand Biggers at Wright-Patterson AFB, Dayton, OH.

Collaboration with a local firm, Superconductive Components, Inc., which is an international manufacturer of bulk superconducting materials such as pressed powder targets for Pulsed Laser Deposition or rf Sputtering of films.

**f) Discoveries, etc.**

The temperature dependence of the vortex pinning strength in films, and probably in bulk materials as well, is dominated by thermal phase, or supercurrent, fluctuations, rather than by the mean-field temperature dependence of the basic superconducting parameters of magnetic penetration depth and Ginzburg-Landau coherence length. The pinning structure in films is columnar rather than point-like or planar.

**g) Additional relevant information.**

None.